

Claims:

1. An ink-jet printing material comprising a support in which both surfaces of a base paper are covered by a polyolefin resin, and an ink-receptive layer containing inorganic fine particles and a hydrophilic binder provided on the support, wherein the ink-jet recording material satisfies a relation of $((B+C)/A) = 0.15$ to 0.45 , where A is a thickness of the base paper; B is a thickness of the polyolefin resin layer at the surface on which the ink-receptive layer is provided; and C is a thickness of the polyolefin resin layer at the opposite surface to that on which the ink-receptive layer is provided, a density of the base paper is 0.60 to 1.05 g/cm³, A is 50 to 300 μm , and B is 5 to 25 μm .

2. The ink-jet recording material according to Claim 1, wherein B is 8 μm or more and less than 20 μm .

3. The ink-jet recording material according to Claim 1, wherein a ratio of B/C is less than 1.

4. The ink-jet recording material according to Claim 3, wherein B is 8 μm or more and less than 20 μm .

5. The ink-jet recording material according to Claim 1, wherein the ink-receptive layer contains the inorganic fine particles in an amount of 50 to 90% by weight.

6. The ink-jet recording material according to Claim 1, wherein the inorganic fine particles are fumed silica which has an average primary particle size of 5 nm to 50 nm.

7. The ink-jet recording material according to Claim 1, wherein the ink-receptive layer contains an amphoteric surfactant.

8. The ink-jet recording material according to Claim 7, wherein

the ink-receptive layer contains the amphoteric surfactant in an amount of 0.1 to 5% by weight.

9. The ink-jet recording material according to Claim 1, wherein
5 the ink-receptive layer contains the hydrophilic binder in an amount of 10 to 25% by weight.

13
12
11
10
9
8
7
6
5
4
3
2
1